


**Ferrocure - 113**  
ผลทดสอบนำยาบ่มชนิดสลายตัว

แบบ วศ. 7



**TEST REPORT**

| Sample's name | Mark / Brand | Laboratory No. |
|---------------|--------------|----------------|
| Ferrocure-113 | -            | YQ.393         |

**Test Results**

|  |       |
|--|-------|
| Water retention : loss of water, kg/m <sup>2</sup> | 2.14  |
| Drying time, min                                   | 15    |
| Non volatile content, %                            | 24.56 |

|                      |  |
|----------------------|--|
| Customer's name      | Ferro Construction Products Co., Ltd.  |
| Customer's address   | 144 Moo 1 Malaiman Rd., Tambol Tungkok, Songphinong District, Supanburi<br>72110 |
| Sample's description | Clear liquid   |
| Test date            | 29 May 2006 – 2 June 2006  |
| Test method          | ASTM C 309-03  |

Approved by  
*Pradab Sawangsri.*  
(Mr.Pradab Sawangsri)  
Scientist 8

Reported by  
*Anon Pomprasit*  
(Mr.Anon Pomprasit)  
Scientist 7