

No. 0307/ **9920**



To FERRO CONSTRUCTION PRODUCT CO.,LTD.

The Department of Science Service presents the test report for the sample named "FERROLASTIC 412 (35 Kg./SET)" Laboratory No. L56/04389.1 as the total of 1 sample with reference to the request No. L56/04389 dated 18 June 2013.

Enclosed herewith the following result avails for your acknowledgement.

Department of Science Service



Physics and Engineering Program

Tel. 0 2201 7130

Fax. 0 2201 7127

E-mail : physics@dss.go.th




## TEST REPORT

Sample's name	Mark / Brand	Laboratory No.
FERROLASTIC 412 (35 Kg./SET)	-	L56/04389.1

### Test Results

Tensile strength, MPa	1.41
Elongation at break, %	238

Customer's name	FERRO CONSTRUCTION PRODUCT CO.,LTD.
Customer's address	144 Moo 1 Malaiman Rd. Thungkok, Songphinong, Suphan Buri 72110
Sample's description	Gray test pieces size approximately 200 x 300 x 2 mm.
Test date	21-24 June 2013
Test method	Tensile strength and Elongation at break : ASTM D412

Approved by  
  
 (Mr. Apinun Ubpakarakun)  
 Scientist, Senior Professional Level

Reported by  
  
 (Mrs. Orasa Onjun)  
 Scientist, Professional Level

This report is only valid for the sample received. The above statement is not intended for advertising purposes and shall not be reproduced or shall not manifest partially without the written permission of the Department of Science Service.